

08-11-00

A

08/10/00



JC695 U.S. PTO

Please type a plus sign (+) inside this box → ☒

Approved for use through 09/30/2000. OMB 0651-0032
 Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE
 Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

UTILITY PATENT APPLICATION TRANSMITTAL (Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))	Attorney Docket No.	6536-118
	First Inventor or Application Identifier	John C. Kralik
	Title	METHODS OF FABRICATING PDLIC.....
	Express Mail Label No.	EL377526578US

APPLICATION ELEMENTS See MPEP chapter 600 concerning utility patent application contents.	ADDRESS TO: Assistant Commissioner for Patents Box Patent Application Washington, DC 20231
---	---

1. <input checked="" type="checkbox"/> * Fee Transmittal Form (e.g., PTO/SB/17) (Submit an original and a duplicate for fee processing) 2. <input checked="" type="checkbox"/> Specification [Total Pages 22] (preferred arrangement set forth below) - Descriptive title of the Invention - Cross References to Related Applications - Statement Regarding Fed sponsored R & D - Reference to Microfiche Appendix - Background of the Invention - Brief Summary of the Invention - Brief Description of the Drawings (if filed) - Detailed Description - Claim(s) - Abstract of the Disclosure 3. <input checked="" type="checkbox"/> Drawing(s) (35 U.S.C. 113) [Total Sheets 6] 4. Oath or Declaration [Total Pages 1] a. <input checked="" type="checkbox"/> Newly executed (original or copy) b. <input type="checkbox"/> Copy from a prior application (37 C.F.R. § 1.63(d)) (for continuation/divisional with Box 16 completed) i. <input type="checkbox"/> DELETION OF INVENTOR(S) Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b). * NOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).	5. <input type="checkbox"/> Microfiche Computer Program (Appendix) 6. Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary) a. <input type="checkbox"/> Computer Readable Copy b. <input type="checkbox"/> Paper Copy (identical to computer copy) c. <input type="checkbox"/> Statement verifying identity of above copies ACCOMPANYING APPLICATION PARTS 7. <input checked="" type="checkbox"/> Assignment Papers (cover sheet & document(s)) 8. <input type="checkbox"/> 37 C.F.R. § 3.73(b) Statement <input type="checkbox"/> Power of (when there is an assignee) <input type="checkbox"/> Attorney 9. <input type="checkbox"/> English Translation Document (if applicable) 10. <input checked="" type="checkbox"/> Information Disclosure <input checked="" type="checkbox"/> Copies of IDS Statement (IDS)/PTO-1449 Citations 11. <input type="checkbox"/> Preliminary Amendment 12. <input type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized) * Small Entity <input type="checkbox"/> Statement filed in prior application, Status still proper and desired 13. <input checked="" type="checkbox"/> Statement(s) <input type="checkbox"/> Status still proper and desired (PTO/SB/09-12) 14. <input type="checkbox"/> Certified Copy of Priority Document(s) (if foreign priority is claimed) 15. <input checked="" type="checkbox"/> Other: <u>Post Card</u>
--	--

16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No: _____
 Prior application information: Examiner _____ Group / Art Unit: _____

For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

<input type="checkbox"/> Customer Number or Bar Code Label	(Insert Customer No. or Attach bar code label here)	or <input checked="" type="checkbox"/> Correspondence address below
Name	Jacob N. Erlich, Esq. Perkins, Smith & Cohen, LLP	
Address	One Beacon Street, 30th Floor	
City	Boston	State MA Zip Code 02108-3106
Country	USA	Telephone 617-854-4000 Fax 617-854-4040

Name (Print/Type)	Jacob N. Erlich	Registration No. (Attorney/Agent)	24,338
Signature		Date	AUG 10, 2000

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

PTO/SB/05 (4/98)
 Approved for use through 09/30/2000. OMB 0651-0032
 Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE
 Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

jc612 U.S. PTO
 09/635606
 08/10/00

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**STATEMENT CLAIMING SMALL ENTITY STATUS
(37 CFR 1.9(f) & 1.27(c))--SMALL BUSINESS CONCERN**

Docket Number (Optional)
6536-118

Applicant, Patentee, or Identifier: John C. Kralik
Application or Patent No.: Not Assigned
Filed or Issued: Herewith
Title: Methods of Fabricating PDLC Optical Devices

I hereby state that I am

- ☐ the owner of the small business concern identified below:
☒ an official of the small business concern empowered to act on behalf of the concern identified below:

NAME OF SMALL BUSINESS CONCERN Wavefront Research, Inc.

ADDRESS OF SMALL BUSINESS CONCERN 616 West Broad Street
Bethlehem, PA 18018

I hereby state that the above identified small business concern qualifies as a small business concern as defined in 13 CFR Part 121 for purposes of paying reduced fees to the United States Patent and Trademark Office. Questions related to size standards for a small business concern may be directed to: Small Business Administration, Size Standards Staff, 409 Third Street, SW, Washington, DC 20416.

I hereby state that rights under contract or law have been conveyed to and remain with the small business concern identified above with regard to the invention described in:

- ☒ the specification filed herewith with title as listed above.
☐ the application identified above.
☐ the patent identified above.

If the rights held by the above identified small business concern are not exclusive, each individual, concern, or organization having rights in the invention must file separate statements as to their status as small entities, and no rights to the invention are held by any person, other than the inventor, who would not qualify as an independent inventor under 37 CFR 1.9(c) if that person made the invention, or by any concern which would not qualify as a small business concern under 37 CFR 1.9(d), or a nonprofit organization under 37 CFR 1.9(e).

Each person, concern, or organization having any rights in the invention is listed below:

- ☒ no such person, concern, or organization exists.
☐ each such person, concern, or organization is listed below.

Separate statements are required from each named person, concern, or organization having rights to the invention stating their status as small entities. (37 CFR 1.27)

I acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement to small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37 CFR 1.28(b))

NAME OF PERSON SIGNING Thomas W. Stone

TITLE OF PERSON IF OTHER THAN OWNER President
c/o Wavefront Research, Inc.

ADDRESS OF PERSON SIGNING Bethlehem, PA 18018

SIGNATURE  DATE 7/26/00

Docket 6536-118

METHODS OF FABRICATING PDLC OPTICAL DEVICES

STATEMENT OF GOVERNMENT INTEREST

This invention was made partially with U.S. Government support under Contract Nos. F30602-95-C-0238 and F30602-98-C-0079 awarded by the U.S. Air Force. The Government has certain rights in the invention.

CROSS REFERENCE TO RELATED APPLICATIONS

This application claims priority of provisional application S.N. 60/148,553 filed August 12, 1999 entitled "Fabrication of Electrooptic Devices" by the present applicant.

FIELD OF THE INVENTION

The present invention relates generally to polymer dispersed liquid crystal (PDLC) films, and, more particularly, to PDLC film fabrication techniques that are useful for the construction of diffractive and non-dispersive optical devices that exhibit high index modulation and low insertion loss.

BACKGROUND OF THE INVENTION

Polymer dispersed liquid crystal (PDLC) materials have been shown useful for the construction of displays and other electrooptic (EO) devices, as pointed out by Drzaic in Liquid Crystal Dispersions (World Scientific Publishing Co., Singapore, 1995). Further, for example, Doane et al. in U.S. Patent 4,688,900 describe the construction and operation of scattering

mode devices based on PDLC films. Those films are comprised of nematic liquid crystal droplets dispersed in a polymer matrix. The resulting devices exhibit an optical response from a highly scattering state to a substantially clear state in response
5 either to an electric field or by thermal means, through control of the PDLC film temperature. While such films are useful for displays or scattering mode polarizers, they are unsuitable for use in diffractive or non-dispersive optical devices since they exhibit high scattering loss in the visible and near infrared.
10 In addition, the switching time of such devices is generally slow, on the order of 1-50 ms.

Sutherland et al. in U.S. Patent 5,942,157 describe how PDLC materials may be formulated and applied to the fabrication of diffractive and refractive EO elements. In that patent, based upon the materials used, the description points out that devices made with materials comprising above 35% liquid crystal content are highly scattering, and therefore are undesirable for EO devices. In addition, such formulations yield materials with very low values of index modulation. For example, Sutherland et al. report in Chemical Materials 5, 1533-38 (1993) that an index modulation of less than 0.003 was measured in transmission gratings made using PDLC materials with low liquid crystal concentration. Consequently, high contrast gratings that
25 operate in the visible could only be realized in extremely thick gratings, on the order of 50 μm thick. PDLC gratings this thick are impractical for use in both the visible and infrared because they require an extremely high switching voltage, and further, because they are inherently lossy due to scattering.

It is therefore an object of this invention to utilize PDLC
30 materials for diffractive and refractive optical components that exhibit extremely low insertion loss.

It is another object of this invention to obtain high index of refraction modulation in photo-curable PDLC films by curing them with a spatially inhomogeneous illumination source. Such films enable the construction of thin, high efficiency, and low-
5 drive-voltage devices.

It is yet another object of this invention to fabricate PDLC-based EO diffractive and refractive devices that display switching times in the microsecond regime.

10 SUMMARY OF THE INVENTION

The objects set forth above as well as further and other objects and advantages of the present invention are achieved by the embodiments of the invention described hereinbelow.

The present invention overcomes the problems of high scattering loss and low index modulation in prior art PDLC films utilized for electrooptic diffractive and refractive optical devices. PDLC materials with greater than 40% nematic liquid crystal content (by weight) are used in this invention to
15 fabricate EO transmission gratings that exhibit negligible scattering loss in the near infrared. In addition, these materials also exhibit large index modulation. Therefore, these features enable the use of these PDLC films for optical switching applications.

For a better understanding of the present invention, together with other and further objects thereof, reference is made to the accompanying drawings and detailed description.
25

BRIEF DESCRIPTION OF THE DRAWINGS

30 Figure 1 is a schematic side view of a PDLC EO device;

Figures 2a, b and c illustrate in schematic fashion a preferred method of fabricating PDLC EO devices;

Figure 3 is a schematic side view of a PDLC device, showing the principle of operation of this invention;

5 Figure 4 illustrates schematically a PDLC film of this invention being utilized as a beamsteering device;

Figure 5 graphically illustrates experimental data that shows large index modulation that is realized in the current invention. The graph shows the transmitted optical beam power
10 through a PDLC grating versus applied electric field for s- and p-polarized light;

Figure 6 graphically illustrates experimental switching data at a wavelength of 1310 nm from a grating fabricated using the prescription described in the present invention;

Figure 7a is a schematic illustration of a refractive PDLC device of this invention that displays variable birefringence;

Figure 7b is an exploded view showing the structure of the PDLC film depicted in Fig. 7a;

Figure 8 schematically illustrates the EO film depicted in Fig. 7a being used as a phase modulator; and
20

Figure 9 schematically illustrates the EO film depicted in Fig. 7a being used as an amplitude modulator.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

25

The present invention relates to techniques for fabricating diffractive and non-dispersive electrooptic (EO), as well as static, devices using polymer dispersed liquid crystal (PDLC) materials. In particular, the fabrication techniques include
30 photo-activated polymerization-induced phase separation utilizing a spatially inhomogeneous illumination source. The

resulting EO devices exhibit low insertion loss, high index modulation, and switching times in the microsecond regime.

Figure 1 illustrates a preferred embodiment of the invention wherein the EO devices are comprised of a PDLC film 12 of thickness T that is preferably approximately 5-20 μm thick or even thicker. The PDLC film 12 is confined in a cell 20 that is comprised of two rigid transparent substrates 14, each coated with a transparent conducting film 16. The transparent conducting films 16 facilitate the application of an electric field across the PDLC film, which is used to vary the optical properties of the PDLC film. Additional transparent dielectric films or multi-layer films 18 may also be coated onto one or both of the transparent conducting films to serve as electrical insulation and/or index matching layers. In an alternative embodiment, the transparent conducting films are not part of the cell, thereby rendering the device static, and not electrically switchable.

The preferred technique for fabricating the device shown in Fig. 1 is shown in Figs. 2a-2c. Figure 2a shows a cell 20 that is similar in construction to the one described above, with thickness T that, as stated above, is preferably approximately 5-20 μm thick or even thicker. This cell is filled with a homogeneous mixture 22 of a nematic liquid crystal material and a pre-polymer material. The nematic liquid crystal concentration is preferably greater than 40% by weight. The preferred nematic liquid crystal is a eutectic mixture that possesses a positive dielectric anisotropy. The preferred pre-polymer material is a photo-curable mixture containing acrylated monomers and oligomers, as well as a suitable photo-initiator. An example of a nematic liquid crystal material that may be utilized to fabricate the EO devices of this invention is one of

the TL-nematics from EM Industries of Hawthorne, NY; while an example of the pre-polymer that may be utilized is PN393, also offered by EM Industries.

Figure 2b shows how to expose the filled cell in order to polymerize, or cure, the pre-polymer component. Two coherent optical beams 30 and 32 are made to intersect inside the cell 20. The beams have equal irradiance and are both s-polarized. In addition, the beams have a wavelength that is near the peak of the absorption band of the photo-initiator component of the pre-polymer mixture. The figure shows that the beams are incident on the cell in the x-y plane at angles of $-\theta$ and $+\theta$ with respect to the cell normal, or y-axis. Under these circumstances, the intersecting beams create an inhomogeneous illumination, or interference pattern 34, inside the cell consisting of alternating bright and dark fringes. The interference pattern is characterized by a grating vector $\Delta\mathbf{k}$ that is parallel with the x-axis. The magnitude of the grating vector, or spatial frequency, is given by $|\Delta\mathbf{k}|=2\pi/\Lambda$, where Λ is the grating period. The grating period is related to the wavelength of the optical beams λ by $\Lambda=\lambda/(2\sin\theta)$.

The spatially periodic illumination pattern 34 shown in Fig. 2b is used to expose the homogeneous nematic/pre-polymer mixture and thereby polymerize the pre-polymer component. A subsequent spatially uniform illumination may be utilized to polymerize any remaining monomers in the cell.

Figure 2c shows the cured film at the conclusion of the exposure process. The resulting PDLC is comprised of regions 42 containing polymer-rich material separated by regions 44 of nematic liquid crystal-rich material. The nematic-rich regions 44 may contain discrete droplets 40 of nematic liquid crystal-rich material, or may contain inter-connected regions that are

filled with nematic liquid crystal-rich material. The exact morphology of these regions 44 depends on the concentration of nematic liquid crystal, the rate of polymerization of the pre-polymer etc. Nevertheless, Fig. 2c shows discrete droplets 40 for the present discussion.

The two distinct regions in the PDLC film form due to phase separation that occurs during the exposure process. The polymer-rich regions 42 reside where the bright fringes occurred during the exposure, and the nematic-rich regions 44 reside where the dark fringes occurred. It should be noted that at the completion of the polymerization process, some nematic liquid crystal remains dissolved in the polymer regions 42, and some pre-polymer material remains in the nematic-rich regions 40. As indicated in Fig. 2c, the spatial period Λ of the PDLC film is the same as that of the illumination pattern in Fig. 2b.

Note that although more difficult to realize at high spatial frequencies, an alternative method for producing a spatially varying illumination in the cell is created by passing a spatially uniform optical beam through a patterned mask in contact with the cell.

Note, too, that the configuration shown in Fig. 2c leads to the formation of an unslanted grating. It is clear, though, from Herwig Kogelnik, Bell System Technical Journal 48(9), 2909-47 (1969), that a grating with slanted planes will result when the absolute values of the incidence angles of the two beams and 32 are not equal.

The method described above allows the fabrication of PDLC films with a large, electrically tunable index of refraction modulation. The operation of these PDLC films is illustrated schematically in Fig. 3. This figure shows a PDLC film in a cell 20 prepared according to the text accompanying Figs. 1 and

2a-c. The spatial period of the PDLC is Λ , and, as described above, the film contains two distinct regions. One region 42 contains polymer-rich material while the second 44 contains nematic liquid crystal-rich material. Again, the nematic liquid crystal-rich regions 44 comprise either of discrete droplets 40 in a polymer matrix (as shown in the figure), or as interconnected regions containing the nematic-rich material. In either case, the nematic directors 46 in these regions 44 are substantially aligned along the grating vector - in this case, the x-axis. This alignment is produced by the flow of liquid crystal that takes place during polymerization in the spatially inhomogeneous illumination source. The resulting high degree of orientational order within the nematic rich regions 44 produces a large index of refraction modulation n_1 within the film plane. The index modulation, as defined by Kogelnik, is given by $n_1 = (n_{LC} - n_p)/2$, where n_{LC} is the index of the nematic-rich regions 44 and n_p is the index of the polymer-rich regions 42.

The optic axis 46 of the nematic-rich regions 44 has a value that is an admixture of the nematic indices, but is weighted most heavily by the extraordinary nematic index n_e . Perpendicular to the droplet axis 48, the nematic-rich regions have an index that is weighted most heavily by the ordinary index n_o of the nematic. In the preferred embodiment, the nematic liquid crystal possesses a positive dielectric anisotropy so that when a sufficiently strong electric field is applied across the PDLC cell along the y-axis, the nematic directors reorient along the field, thereby reorienting the optic axis 46 of the nematic-rich regions to lie along the y-axis.

Additionally, the preferred embodiment should utilize a nematic that has n_o approximately equal to n_p and $n_e > n_p$. In this case, the index modulation n_i is a maximum in the absence of an applied field, and zero under a sufficiently strong field as experienced by light polarized in the x-y plane. For light that is orthogonal to this, n_i is nearly zero, and further, this value does not depend on the amplitude of the applied switching field.

These concepts have been substantiated by experimental demonstrations described in the examples below. The examples serve to illustrate several modes of the invention and are not to be construed as a limitation of the present invention.

EXAMPLE 1

Figure 4 is a schematic diagram of an electrically switched transmission grating fabricated with PDLC materials as provided by this invention. This EO beamsteering device was designed to operate in the near infrared; however, similar switches can operate at select wavelengths throughout the visible to IR. The material utilized to make the grating contained a mixture of 67% (by weight) of a commercially available nematic liquid crystal and 33% (by weight) of a commercially available pre-polymer comprising acrylated monomers and oligomers with a photoinitiator that is sensitive in the UV. The PDLC film was formed by introducing the homogenous nematic/pre-polymer mixture into a cell consisting of two glass substrates coated with a transparent indium-tin-oxide (ITO) conducting film. In addition, the ITO films were partially coated with a dielectric insulator. Spherical polymer spacers were used to separate the glass substrates; the cell thickness T was 15.4 μm .

A PDLC grating with a period $\Lambda=1.92 \mu\text{m}$ was recorded in the material via the techniques described earlier. The grating formation process was monitored with a probe laser beam, and the exposure was stopped after the change in probe beam diffraction efficiency reached a suitably small value.

The EO grating was designed to diffract light at a wavelength of 1310 nm through a Bragg angle of 20 degrees (in air). Light incident on the grating at the Bragg angle was either transmitted through the grating in the $m=0$ order or diffracted into the $m=+1$ order, depending on the value of the applied electric field across the cell. The diffraction efficiency was measured by monitoring the $m=0$ beam as a function of applied electric field for different beam polarization. Here, *s*-polarized light refers to an optical wave with an electric field vector oscillating into and out of the plane of the figure, while *p*-polarized light refers to an optical wave with an electric field vector lying in the plane of the figure.

The PDLC grating was switched by applying an electric field across the cell. This was accomplished by attaching the output of an electrical amplifier to the cell via the ITO films on the two substrates.

Grating switching results are presented in Fig. 5. This graph shows the diffraction efficiency of the $m=0$ diffracted beam as a function of applied electric field for *s*- and *p*-polarized light. Here, the diffraction efficiency represents the amount of optical power measured in the $m=0$ beam, normalized to the total power measured in both the $m=0$ and $+1$ orders. Additionally, the electric field was derived by dividing the applied voltage value across the cell by the cell thickness. It is evident from this data that the switched grating is effective

in switching p-polarized light only. This lends strong support to statements made earlier about the high degree of orientational order in the nematic-rich regions throughout the film.

5 Figure 5 also demonstrates the high index modulation that can be achieved in PDLC systems with greater than 40% liquid crystal content. Indeed, this grating is over-modulated since it modulates the p-polarized beam in excess of 100%. That is, the grating modulation is near zero for a high applied field and
10 it reaches a maximum value when the field amplitude is zero. According to a result found in the article by Kogelnik, the $m=0$ order diffraction efficiency $\eta_p(m=0)$ for p-polarized light is given by

$$\eta_p(m=0) = \cos^2 v_p$$

where

$$v_p = \frac{\pi n_1 T \cos(2\theta)}{\lambda \cos \theta} .$$

Based on the data in Fig. 5, the grating has $v_p = 2.4$ radians and $n_1 = 0.069$ when the field is off. This value of index modulation is some 20 times larger than that achieved using low-nematic-concentration PDLC gratings.

25 Two additional features of the switched grating are noteworthy. First, the switching time of the grating was about 400 μ s. This value is more than two orders of magnitude faster than that of mechanical beamsteering switches and more than one order of magnitude faster than thermo-optic switches, both of

which are widely used in the telecommunications arena. The second noteworthy feature is the low value of insertion loss exhibited by the switched grating. In the example shown above, the insertion loss was dominated by Fresnel reflection loss from the two air-glass interfaces of the switching element. If this loss is minimized through the use of anti-reflection coatings, the ultimate insertion loss could be engineered to be just a few percent per switched grating.

EXAMPLE 2

In this example, a low loss, high contrast electrically switched PDLC diffraction grating is demonstrated with a switching time of just 70 μ s. The PDLC constituents used are the same as that described in Example 1; however, the nematic/pre-polymer ratio was changed to 1:1 by weight. This lower liquid crystal concentration led to smaller confinement spaces for the nematic-rich material in the PDLC film, and in turn, a faster switching time.

A grating structure was formed in the PDLC film in the same manner as in Example 1, resulting in a grating period of 1.92 μ m. The grating thickness in this example was 13.0 μ m and the incident optical beam had a wavelength of 1310 nm and was p-polarized. Figure 6 shows graphically the diffraction efficiency of the m=0 and +1 beams versus time during a switching event that occurs when a voltage pulse is applied across the PDLC cell from time t=0 to t=725 μ s. The switching time, which is defined as the average time to transition from the 10% to 90% levels in the efficiency data for the m=0 and m=+1 optical signals after the applied voltage is removed, was measured to be just 70 μ s. In addition, the insertion loss of

the switch was just a few percent and the contrast ratio was nearly 18 dB.

EXAMPLE 3

5

10

The material systems and fabrication technique described in relation to the first two examples were applied to the construction of an EO variable retarder. This retarder is based on a PDLC transmission grating that has a grating period smaller than the wavelength of light to be modulated.

15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500

25

A schematic diagram of a PDLC variable retarder is shown in Figs. 7a and 7b. Figure 7a shows the PDLC film 80 in the xy -plane with light incident on the device propagating along the z -axis. The grating vector 82 is parallel to the x -axis. The expanded view in Fig. 7b (labeled A in Fig. 7a shows the underlying structure of the EO film. The film is characterized by thickness T and spatial period Λ ; Λ is designed to be smaller than the wavelength of the optical beam to be modulated. The PDLC film contains two distinct regions: polymer-rich regions 90, and nematic liquid crystal-rich regions 92. The presence of a nematic liquid crystal in the film allows it to experience a change in index of refraction on application of an electric field of sufficient amplitude and duration. As was the case in the diffraction gratings described in the text accompanying Fig. 3, the liquid crystal-rich regions 92 exhibit a high degree of orientational order throughout the PDLC film.

30

The effective film indices of refraction n_x and n_y , along the x - and y -axes, respectively, can be estimated knowing the film morphology and the optical indices of the constituent materials. The index of refraction of the material in the polymer-rich regions is taken to be n_1 , where n_1 represents an

average value derived from the optical indices of the polymeric material and the liquid crystal material. Specifying the optical properties of the liquid crystal-rich regions is more involved since they contain a high concentration of birefringent nematic liquid crystal material that can reorient under the influence of an applied field. The liquid crystal-rich regions are specified by indices n_{2x} and n_{2y} along the x- and y-axes, respectively. It was shown in Example 1 that the index n_{2y} does not change appreciably under the influence of an applied electric field; however, index n_{2x} changes significantly under the influence of an electric field. With no field applied, the index n_{2x} represents an average value derived from the index of the polymer-rich material and the extraordinary index n_e of the nematic molecules. Under the influence of a sufficiently strong field, though, the nematic molecules reorient so as to align with the substrate normal. In this case, n_{2x} represents an average value derived from the index of the polymer-rich material and the ordinary index n_o of the nematic. Since for most nematic liquid crystal materials $n_e > n_o$, n_{2x} is larger in the absence of an applied field than when a field is applied.

In *Applied Physics Letters* 42(6), 492 (1983), Flanders reports on constructing a static birefringent plate using a composite dielectric structure. The formalism described therein can be tailored to provide a description of the PDLC film shown in Figs. 7a and 7b. Starting from the Flanders work, the effective indices n_x and n_y of a spatially periodic composite film with a 50% duty cycle and a period much smaller than that of an optical field - i.e. one with $\Lambda \ll \lambda$ - can be written

$$n_x = \frac{1}{\sqrt{\frac{1}{2n_1^2} + \frac{1}{2n_{2x}^2}}}, \quad n_y = \sqrt{\frac{n_1^2}{2} + \frac{n_{2y}^2}{2}}.$$

where the definitions of the indices n_1 , n_{2x} , and n_{2y} are given in the previous paragraph. One of the results of the Flanders work is that the formalism seems to describe the case where $\Lambda \ll \lambda$ is not strictly met, as long as $\Lambda < \lambda/2$ so that no diffracted orders propagate. As mentioned above, a PDLC film exhibits continuously tunable birefringence $\delta n = n_x - n_y$ through its dependence on n_{2x} .

A PDLC retarder was constructed using materials similar to those described in Example 1. The nematic/pre-polymer ratio was 2:1; the grating period was $\Lambda = 0.5 \mu\text{m}$; and the film thickness was $4.9 \mu\text{m}$. The film birefringence was measured in a standard Kerr set-up using a probe beam with a wavelength of $0.6328 \mu\text{m}$. Note that negligible optical power was diffracted by the film for light incident normal to the film plane. In this situation, the film birefringence varied between $\delta n = 0.048$ and $\delta n = 0$, as an applied electric field was increased from zero to a value sufficient to reorient the nematic dispersed in the film. The switching time of the waveplate was just a few hundred microseconds; however, it is conceivable that this can be reduced to less than $100 \mu\text{s}$ with further optimization.

The variable retarder film shown in Fig. 7a may be utilized as either a phase or amplitude modulator. Figure 8 demonstrates how the film may be utilized as a phase modulator. The film is characterized by thickness T and grating vector 112 , indicated by the dashed line in the figure. An optical beam 114 of unit amplitude and wavelength λ is incident normal to the film plane

from the left side of the figure; the beam is linearly polarized parallel to the grating vector. The optical beam 116 acquires a phase shift of $\Delta\phi = 2\pi n_x L / \lambda$ on passing through the film on the right side of the figure. Since the film index n_x depends on the field-dependent index n_{2x} , the optical phase change can be varied electrically.

In a similar manner, the PDLC film depicted in Fig. 7a may be utilized as an amplitude modulator. Figure 9 illustrates how this is accomplished. Again, the PDLC film is characterized by its thickness T and grating vector 132, and an optical beam of wavelength λ is incident on the film perpendicular to the film plane. In this case, though, the incident optical beam 134 is linearly polarized in a plane that makes an angle of 45 degrees to the grating vector. Light exiting the PDLC film next encounters a polarizer 138 with its transmission axis 140 aligned either parallel or perpendicular to the plane of polarization of the incident optical beam. In the example shown in Fig. 9, the transmission axis 140 of the polarizer 138 is oriented parallel to the plane of polarization of the incident beam. In this case, the amplitude 142 of the light exiting the polarizer is proportional to $\sin(\pi \delta n L / \lambda)$. Hence, as the film birefringence δn changes under the influence of an applied field, the optical output power of the beam may be varied from a maximum of unity to a minimum of zero.

Although the invention has been described with respect to various embodiments, it should be realized this invention is also capable of a wide variety of further and other embodiments within the spirit and scope of the appended claims.

What is claimed is:

CLAIMS

1. A method of fabricating an electrooptic device, comprising the steps of:

5 providing a nematic liquid crystal;

providing a photo-curable pre-polymer mixture;

10 mixing said nematic liquid crystal with said photo-curable pre-polymer mixture to form a homogeneous nematic/pre-polymer mixture, with said nematic liquid crystal being greater than 40% (by weight) of said combined homogeneous mixture;

providing a cell comprising a pair of spaced apart transparent substrates that are each coated with a transparent conductive layer;

15 filling said cell with said homogeneous nematic/pre-polymer mixture; and

20 photo-curing said nematic/pre-polymer mixture using a spatially inhomogeneous illumination source thereby creating the electrooptic device in the form of a polymer dispersed liquid crystal (PDLC) exhibiting low scattering loss and high index modulation.

2. The method as defined in claim 1 wherein said nematic liquid crystal possesses a positive dielectric anisotropy.

25 3. The method as defined in claim 1 wherein said nematic liquid crystal is a eutectic mixture.

4. The method as defined in claim 1 wherein said substrates are separated by approximately 5-20 μm .

5. The method as defined in claim 1 wherein said PDLC is comprised of a dispersion of discrete droplets containing nematic liquid crystal-rich material in a polymer-rich matrix.

5 6. The method as defined in claim 1 wherein said PDLC is comprised of regions of inter-connected spaces that are filled with nematic liquid crystal-rich material.

10 7. The method as defined in claim 1 further comprising the step of deriving said spatially inhomogeneous illumination source used to photo-cure the nematic/pre-polymer mixture from the interference of two coherent optical beams within said cell.

8. The method as defined in claim 7 wherein said coherent optical beams each have a wavelength in the ultraviolet spectrum.

9. The method as defined in claim 7 wherein said interfering optical beams are incident symmetrically about a direction normal to said cell in order to form said PDLC as an unslanted PDLC transmission grating.

10. The method as defined in claim 9 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a grating period that is greater than half the wavelength of the light to be diffracted by the PDLC transmission grating during use of said transmission grating.

11. The method as defined in claim 9 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a spatial frequency that is sufficiently high to prohibit propagating diffracted orders for

normal incident light, thereby creating an electrooptic retarder with electrically tunable birefringence.

12. The method as defined in claim 10 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high degree of orientational order and has its nematic director substantially aligned along its grating vector when no drive field is applied across said cell.

13. The method as defined in claim 11 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high degree of orientational order and has its nematic director substantially aligned along its grating vector when no drive field is applied across said cell.

14. A method of fabricating a static optical device, comprising the steps of:

providing a nematic liquid crystal;

providing a photo-curable pre-polymer mixture;

mixing said nematic liquid crystal with said photo-curable pre-polymer mixture to form a homogeneous nematic/pre-polymer mixture, with said nematic liquid crystal being greater than 40% (by weight) of said combined homogeneous mixture;

providing a cell comprising a pair of spaced apart transparent substrates;

filling said cell with said homogeneous nematic/pre-polymer mixture; and

photo-curing said nematic/pre-polymer mixture using a spatially inhomogeneous illumination source thereby creating a static optical device in the form of a polymer dispersed liquid crystal (PDLC) exhibiting low scattering loss and high index modulation.

15. The method as defined in claim 14 wherein said substrates are separated by approximately 5-20 μm .

5 16. The method as defined in claim 14 wherein said PDLC is comprised of a dispersion of discrete droplets containing nematic liquid crystal-rich material in a polymer-rich matrix.

10 17. The method as defined in claim 14 wherein said PDLC is comprised of regions of inter-connected spaces that are filled with nematic liquid crystal-rich material.

15 18. The method as defined in claim 14 further comprising the step of deriving said spatially inhomogeneous illumination source used to photo-cure the nematic/pre-polymer mixture from the interference of two coherent optical beams within said cell.

20 19. The method as defined in claim 18 wherein said coherent optical beams each have a wavelength in the ultraviolet spectrum.

25 20. The method as defined in claim 18 wherein said interfering optical beams are incident symmetrically about a direction normal to said cell in order to form said PDLC as an unslanted PDLC transmission grating.

30 21. The method as defined in claim 20 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a grating period that is greater than half the wavelength of the light to be diffracted by the PDLC transmission grating during use of said transmission grating.

22. The method as defined in claim 20 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a spatial frequency that is
5 sufficiently high to prohibit propagating diffracted orders for normal incident light, thereby creating a retarder.

23. The method as defined in claim 21 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high
10 degree of orientational order and has its nematic director substantially aligned along its grating vector.

24. The method as defined in claim 22 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high
15 degree of orientational order and has its nematic director substantially aligned along its grating vector.

25. The method as defined in claim 14 wherein said nematic liquid crystal is a eutectic mixture.
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995

ABSTRACT OF THE DISCLOSURE

A method of fabricating an optical device by providing a nematic liquid crystal; providing a photo-curable pre-polymer mixture; mixing the nematic liquid crystal with the photo-curable pre-polymer mixture to form a homogeneous nematic/pre-polymer mixture, with the nematic liquid crystal representing greater than 40% (by weight) of the combined homogeneous mixture. Providing a cell including a pair of transparent substrates that are each coated with a transparent conductive layer when creating an electrooptic device and omitting the conductive layers when creating a static device. Separating the substrates by approximately 5-20 μm or greater; filling the cell with the homogeneous nematic/pre-polymer mixture; and photo-curing the nematic/pre-polymer mixture using a spatially inhomogeneous illumination source thereby forming a polymer dispersed liquid crystal (PDLC) film exhibiting low scattering loss and high index modulation.

6536-118-PatApp4




FIGURE 1




FIGURE 2a




FIGURE 2b




FIGURE 2c




FIGURE 4




FIGURE 5




FIGURE 6




FIGURE 7a




FIGURE 7b




FIGURE 8




FIGURE 9

[illegible]

Please type a plus sign (+) inside this box → ☐

PTO/SB/01 (12-97)

Approved for use through 9/30/00. OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63) <input checked="" type="checkbox"/> Declaration Submitted with Initial Filing OR <input type="checkbox"/> Declaration Submitted after Initial Filing (surcharge (37 CFR 1.16 (e)) required)	Attorney Docket Number	6536-118
	First Named Inventor	John C. Kralik
	COMPLETE IF KNOWN	
	Application Number	/
	Filing Date	Herewith
	Group Art Unit	
	Examiner Name	

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

METHODS OF FABRICATING PDLA OPTICAL DEVICES

the specification of which (Title of the Invention)

☒ is attached hereto

OR

☐ was filed on (MM/DD/YYYY) as United States Application Number or PCT International

Application Number and was amended on (MM/DD/YYYY) (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				YES	NO
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto:

I hereby claim the benefit under 35 U.S.C. 119(e) of any United States provisional application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)	<input type="checkbox"/> Additional provisional application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.
60/148,553	08/12/1999	

[Page 1 of 2]

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

Please type a plus sign (+) inside this box → ☐

PTO/SB/01 (12-97)
Approved for use through 9/30/00. OMB 0651-0032
Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

DECLARATION — Utility or Design Patent Application

I hereby claim the benefit under 35 U.S.C. 120 of any United States application(s), or 365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR 1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application or PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet PTO/SB/02B attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

☐ Customer Number

OR

☒ Registered practitioner(s) name/registration number listed below

Place Customer
Number Bar Code
Label here

Name	Registration Number	Name	Registration Number
Jerry Cohen	20,522	Christine M. Kuta	38,001
Harvey Kaye	18,978	Jacob N. Erlich	24,338
Stephen Y. Chow	31,338	Chester A. Bisbee	44,538

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet PTO/SB/02C attached hereto.

Direct all correspondence to: ☐ Customer Number or Bar Code Label

OR ☒ Correspondence address below

Name	Jerry Cohen				
Address	c/o Perkins, Smith & Cohen, LLP				
Address	One Beacon Street, 30th Floor				
City	Boston	State	MA	ZIP	02108-3106
Country	USA	Telephone	617-854-4000	Fax	617-854-4040

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor:

☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))		Family Name or Surname	
John C.		Kralik	
Inventor's Signature	Date		8/9/00
Residence: City	Lansdale	State	PA
		Country	USA
Post Office Address	c/o Wavefront Research, Inc.		
Post Office Address	616 West Broad Street		
City	Bethlehem	State	PA
		ZIP	18018
		Country	USA

☐ Additional inventors are being named on the supplemental Additional Inventor(s) sheet(s) PTO/SB/02A attached hereto